

### Material

Two layer construction:

Face material Coextruded clear Polyethylene film (not corona treated).

Backing material Transparent BOPP film.

Basis Weight	147 g/m <sup>2</sup>	ISO 536
Caliper	160 µm	ISO 534
Caliper Face	110 my	ISO 534
Caliper backing	50 my	ISO 534
Density	0.925 (PE film) gr/cc	ASTM D792

Service temp. -20 to +50 °C

Application temperature range >5 °C

Cling Adhesion	.01 N/25mm	FTM1 on glass
Shrinkage MD (1 min after separation from backing film)	-2 %	internal method
Shrinkage CD (1 min after separation from backing film)	1 %	internal method

### Applications and use

FASSON STATIC CLING PE CL-110 is a cling film of Polyethylene, that clings without adhesive on smooth, glossy surfaces (like glass, PET, PMMA, PC, ...). It could be easily removed and leaves no residues (in combination with laquers and plastics the compatibility must be tested). It could be reused / reapplied. Main application is protection of delicate surfaces.

The material has been tested against the following regulations and standards: 2011/65/EU (RoHS - restriction of hazardous substances 06/2011); EN 71-3 (Safety of toys, migration of certain elements 12/1988).

### Conversion & printing

The film requires corona treatment for printing with UV letterpress, UV screen printing and gravure. Testing for suitability between media, printers and inks is always recommended prior to use.

Good die cutting characteristics with BOPP liner.

### Special Approvals

#### CAUTION


Low optical Transparency of PE film. Slightly hazy, possibly small scratches

### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AS990

### Fasson® STATIC CLING PE CL-110



STATIC CLING PE CL-110



*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery



©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are



Inspired Brands.  
Intelligent World.™

Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.